

1. Product and Company Identification

- **PRODUCT NAME:** Staron® solid surfaces sheet
- **COMPANY:** Samsung SDI
- **EMERGENCY TELEPHONE:** 82-61-689-1531
- **ADDRESS:** Yeosu Plant, Chemicals Division, Samsung SDI,
62, Pyong Yo-Dong, Yeosu-Shi, Cheon Nam, Korea

2. Composition/information on ingredients

- **INGREDIENT:** Acrylic Polymer
- **INGREDIENT SEQUENCE NUMBER:** 01
- **PERCENT:** 40 ~ 45
- **CAS NUMBER:** 9011 - 14 - 7
- **INGREDIENT:** Hydrated Alumina, Aluminum Hydroxide, Aluminum Trihydroxide
- **INGREDIENT SEQUENCE NUMBER:** 02
- **PERCENT:** 55 ~ 60
- **NIOSH(RTECS) NUMBER:** BD094000
- **CAS NUMBER:** 21645 - 51 - 2

3. Hazards identification

Staron® solid surfaces sheet is not hazardous when shipped. However, operations such as sawing, routing, drilling and sanding can generate dust. High concentrations of dust can irritate eyes, nose and respiratory passages and cause coughing and sneezing. Even though there are no exposure limits established for dust from Staron® solid surfaces sheet, avoid breathing dust. (See details in the Exposure Controls/Personal Protection section of this MSDS)

Staron® solid surfaces sheet does not off-gas at room temperature. At higher temperature, a small amount of methyl methacrylate can be released. The amount depends on temperature, time and other variables. Methyl methacrylate vapors can irritate eyes, skin, nose and throat and can cause allergic skin rashes. Over exposure to methyl methacrylate vapors can cause headaches, nausea, weakness, lung irritation and shortness of breath. Individuals with pre-existing lung or skin problems may be more susceptible to the effects of over exposure to methyl methacrylate.

4. First Aid Measures

- **INHALATION:** Move to fresh air
- **EYE CONTACT:** Not applicable
- **SKIN CONTACT:** Not applicable
- **INGESTION:** Not applicable

5. Fire Fighting Measures

- **AFTER SPILLAGE/LEAKAGE/GAS LEAKAGE:**
Keep away from all of ignition sources. Ensure adequate ventilation. Use personal protective equipment. Soak up with inert absorbent material. Clean with detergents. Avoid solvents.
- **EXTINGUISHING MEDIA:**
Dry powder, foam, carbon dioxide, water spray

This Technical Bulletin is intended to provide guidelines for optimal fabrication, installation, and performance of Samsung products mentioned. Though the information contained herein is deemed reliable, none of the contents--including but not limited to the instructions, techniques, graphics, and recommendations--is to be understood as implying legal liability of fitness for a specific purpose, any other type of warranty, or being complete or absolute in its range and nature of information.

Depending on the user's particular application, all necessary measures must be taken to verify and test the adequacy for such needs or application. Any information or recommendation herein is strictly for purposes of reference and as such, Samsung SDI assumes no responsibility for its suitability or accuracy or the use of such information for products other than Samsung Staron® solid surfaces & Radianz® quartz surfaces.

6. Accidental Release Measures

Review **FIRE FIGHTING MEASURES** and **HANDLING AND STORAGE** sections before proceeding with clean-up. Use appropriate personal protective equipment during clean-up.

7. Handling and Storage

- **HANDLING:** Staron® solid surfaces sheet should be unloaded with a forklift or other lifting device capable of handling pallets safely. If a lifting device is not available, always carry single sheet in the vertical position, and wear heavy-duty protective gloves and proper safety shoes. Carrying should be done by two people facing each other on short sides with one hand under to support and the other hand on top to control the sheet.
- **STORAGE:** Keep capable of handling sheet flat and evenly supported at temperatures between 15° ~ 23°C (59° ~ 73°F), in a dry and well-ventilated indoor area.

8. Exposure Controls/Personal Protection

- **TECHNICAL PROTECTIVE MEASURES:**

Provide for appropriate exhaust ventilation and dust collection at machinery.

- **PERSONAL PROTECTIVE EQUIPMENT:**

RESPIRATION (DURING MACHINING OPERATION): In case of insufficient ventilation, wear appropriate respiratory equipment in compliance with local regulations.

EYES (DURING MACHINING OPERATION): Use tightly fitting safety goggles or face-shield.

HANDS (DURING MACHINING OPERATION): Wear protective gloves.

OTHERS (DURING MACHINING OPERATION): Use ear protection, safety shoes. Those who are highly sensitivity should take precautions due to possible eye, nose or throat irritation from Staron® solid surfaces dust and fumes.

9. Physical and Chemical Properties

- **FORM:** Solid sheet
- **COLOR:** Various
- **ODOR:** None
- **BOILING POINT:** Not Applicable
- **MELTING POINT:** Not Applicable
- **SPECIFIC GRAVITY (WATER = 1):** 1.6 ~ 1.8
- **VAPOR PRESSURE (mmHg):** Not Applicable
- **VAPOR DENSITY (Air = 1):** Not Applicable
- **SOLUBILITY IN WATER:** Insoluble
- **pH:** Not Applicable
- **FLASH POINT:** Not Applicable
- **IGNITION TEMPERATURE:** Not Applicable
- **EXPLOSION LIMITS:** Lower = Not Applicable
Upper = Not Applicable

This Technical Bulletin is intended to provide guidelines for optimal fabrication, installation, and performance of Samsung products mentioned. Though the information contained herein is deemed reliable, none of the contents--including but not limited to the instructions, techniques, graphics, and recommendations--is to be understood as implying legal liability of fitness for a specific purpose, any other type of warranty, or being complete or absolute in its range and nature of information.

Depending on the user's particular application, all necessary measures must be taken to verify and test the adequacy for such needs or application. Any information or recommendation herein is strictly for purposes of reference and as such, Samsung SDI assumes no responsibility for its suitability or accuracy or the use of such information for products other than Samsung Staron® solid surfaces & Radianz® quartz surfaces.

10. Stability and Reactivity

- **THERMAL DECOMPOSITION PRODUCT:**

Frictional heat generated from sawing and routing Staron® solid surfaces sheet can reach or exceed a temperature of 300°C. This is high enough to release a small amount of methyl methacrylate vapor.

- **HAZARDOUS DECOMPOSITION PRODUCT:** Carbon monoxide, methyl methacrylate monomer, smoke
- **HAZARDOUS REACTION:** None
- **FURTHER INFORMATION:** Sprayed mist may be flammable at temperature below the flash point.

11. Toxicological Information

- **METHYL METHACRYLATE**

TLV-TWA = 100 ppm = 410 mg/m³; ACGIH (1991-2)

LD50/oral/rat = 7872 mg/kg; RTECS, 47796

Methyl methacrylate can be present on the cutting tool face at a concentration exceeding the TLV of 100 ppm. However, it dissipates to very low levels with good ventilation.

12. Ecological Information

Staron® solid surfaces sheet is manufactured by Samsung SDI in accordance with ISO-14001 standards.

13. Disposal Considerations

Can be landfilled or incinerated, when in compliance with local regulations.

14. Transport Information

Not classified as dangerous in the meaning of transport regulations.

15. Regulatory Information

- **U.S. FEDERAL REGULATIONS**

TSCA Inventory Status: In compliance with TSCA Inventory requirements for commercial purposes.

16. Other Information

- **ADDITIONAL INFORMATION**

Do not use in medical applications involving permanent implantation in the human body.

We hereby certify that the above statements are accurate.

Signature/Issued Date: Samsung SDI

Staron® solid surfaces

Samsung SDI

This Technical Bulletin is intended to provide guidelines for optimal fabrication, installation, and performance of Samsung products mentioned. Though the information contained herein is deemed reliable, none of the contents--including but not limited to the instructions, techniques, graphics, and recommendations--is to be understood as implying legal liability of fitness for a specific purpose, any other type of warranty, or being complete or absolute in its range and nature of information.

Depending on the user's particular application, all necessary measures must be taken to verify and test the adequacy for such needs or application. Any information or recommendation herein is strictly for purposes of reference and as such, Samsung SDI assumes no responsibility for its suitability or accuracy or the use of such information for products other than Samsung Staron® solid surfaces & Radianz® quartz surfaces.

1. Product and Company Identification

- **PRODUCT NAME:** Staron® solid surfaces sinks and bowls
- **COMPANY:** Samsung SDI
- **EMERGENCY TELEPHONE:** 82-61-689-1531
- **ADDRESS:** Yeosu Plant, Chemicals Division, Samsung SDI
62, Pyong Yo-Dong, Yeosu-Shi, Cheon Nam, Korea

2. Composition/information on ingredients

- **INGREDIENT:** Acrylic Polymer
- **INGREDIENT SEQUENCE NUMBER:** 01
- **PERCENT:** 40 ~ 45
- **CAS NUMBER:** 9011 - 14 - 7
- **INGREDIENT:** Hydrated Alumina, Aluminum Hydroxide, Aluminum Trihydroxide
- **INGREDIENT SEQUENCE NUMBER:** 02
- **PERCENT:** 55 ~ 60
- **NIOSH(RTECS) NUMBER:** BD094000
- **CAS NUMBER:** 21645 - 51 - 2

3. Hazards identification

Staron® solid surfaces Sinks and Bowls is not hazardous when shipped. However, operations such as sawing, routing, drilling and sanding can generate dust. High concentrations of dust can irritate eyes, nose and respiratory passages and cause coughing and sneezing. Even though there are no exposure limits established for dust from Staron® solid surfaces Sinks and Bowls, avoid breathing dust. (See details in the Exposure Controls/Personal Protection section of this MSDS)

Staron® solid surfaces Sinks and Bowls does not off-gas at room temperature. At higher temperature, a small amount of methyl methacrylate can be released. The amount depends on temperature, time and other variables. Methyl methacrylate vapors can irritate eyes, skin, nose and throat and can cause allergic skin rashes. Over exposure to methyl methacrylate vapors can cause headaches, nausea, weakness, lung irritation and shortness of breath. Individuals with pre-existing lung or skin problems may be more susceptible to the effects of over exposure to methyl methacrylate.

4. First Aid Measures

- **INHALATION:** Move to fresh air
- **EYE CONTACT:** Not applicable
- **SKIN CONTACT:** Not applicable
- **INGESTION:** Not applicable

5. Fire Fighting Measures

- **AFTER SPILLAGE/LEAKAGE/GAS LEAKAGE:**
Keep away from all of ignition sources. Ensure adequate ventilation. Use personal protective equipment. Soak up with inert absorbent material. Clean with detergents. Avoid solvents.
- **EXTINGUISHING MEDIA:**
Dry powder, foam, carbon dioxide, water spray

This Technical Bulletin is intended to provide guidelines for optimal fabrication, installation, and performance of Samsung products mentioned. Though the information contained herein is deemed reliable, none of the contents--including but not limited to the instructions, techniques, graphics, and recommendations--is to be understood as implying legal liability of fitness for a specific purpose, any other type of warranty, or being complete or absolute in its range and nature of information.

Depending on the user's particular application, all necessary measures must be taken to verify and test the adequacy for such needs or application. Any information or recommendation herein is strictly for purposes of reference and as such, Samsung SDI assumes no responsibility for its suitability or accuracy or the use of such information for products other than Samsung Staron® solid surfaces & Radianz® quartz surfaces.

6. Accidental Release Measures

Review **FIRE FIGHTING MEASURES** and **HANDLING AND STORAGE** sections before proceeding with clean-up. Use appropriate personal protective equipment during clean-up.

7. Handling and Storage

- **HANDLING:** Staron® solid surfaces Sinks and Bowls should be unloaded with a forklift or other lifting device capable of handling pallets safely.
- **STORAGE:** Keep Staron® solid surface Sinks and Bowls evenly supported at temperatures between 15° ~ 23°C (59° ~ 73°F), in a dry and well-ventilated indoor area.

8. Exposure Controls/Personal Protection

- **TECHNICAL PROTECTIVE MEASURES:**
Provide for appropriate exhaust ventilation and dust collection at machinery.
- **PERSONAL PROTECTIVE EQUIPMENT:**
RESPIRATION (DURING MACHINING OPERATION): In case of insufficient ventilation, wear appropriate respiratory equipment in compliance with local regulations.
EYES (DURING MACHINING OPERATION): Use tightly fitting safety goggles or face-shield.
HANDS (DURING MACHINING OPERATION): Wear protective gloves.
OTHERS (DURING MACHINING OPERATION): Use ear protection, safety shoes. Those who are highly sensitivity should take precautions due to possible eye, nose or throat irritation from Staron® solid surfaces dust and fumes.

9. Physical and Chemical Properties

- **FORM:** Solid shape
- **COLOR:** Various
- **ODOR:** None
- **BOILING POINT:** Not Applicable
- **MELTING POINT:** Not Applicable
- **SPECIFIC GRAVITY (WATER = 1):** 1.6 ~ 1.8
- **VAPOR PRESSURE (mmHg):** Not Applicable
- **VAPOR DENSITY (Air = 1):** Not Applicable
- **SOLUBILITY IN WATER:** Insoluble
- **pH:** Not Applicable
- **FLASH POINT:** Not Applicable
- **IGNITION TEMPERATURE:** Not Applicable
- **EXPLOSION LIMITS:** Lower = Not Applicable
Upper = Not Applicable

This Technical Bulletin is intended to provide guidelines for optimal fabrication, installation, and performance of Samsung products mentioned. Though the information contained herein is deemed reliable, none of the contents--including but not limited to the instructions, techniques, graphics, and recommendations--is to be understood as implying legal liability of fitness for a specific purpose, any other type of warranty, or being complete or absolute in its range and nature of information.

Depending on the user's particular application, all necessary measures must be taken to verify and test the adequacy for such needs or application. Any information or recommendation herein is strictly for purposes of reference and as such, Samsung SDI assumes no responsibility for its suitability or accuracy or the use of such information for products other than Samsung Staron® solid surfaces & Radianz® quartz surfaces.

10. Stability and Reactivity

- **THERMAL DECOMPOSITION PRODUCT:**

Frictional heat generated from sawing and routing Staron® solid surfaces Sinks and Bowls can reach or exceed a temperature of 300°C. This is high enough to release a small amount of methyl methacrylate vapor.

- **HAZARDOUS DECOMPOSITION PRODUCT:** Carbon monoxide, methyl methacrylate monomer, smoke

- **HAZARDOUS REACTION:** None

- **FURTHER INFORMATION:** Sprayed mist may be flammable at temperature below the flash point.

11. Toxicological Information

- **METHYL METHACRYLATE**

TLV-TWA = 100 ppm = 410 mg/m³; ACGIH (1991-2)

LD50/oral/rat = 7872 mg/kg; RTECS, 47796

Methyl methacrylate can be present on the cutting tool face at a concentration exceeding the TLV of 100 ppm. However, it dissipates to very low levels with good ventilation.

12. Ecological Information

Staron® solid surfaces sinks and bowls is manufactured by Samsung SDI in accordance with ISO-14001 standards.

13. Disposal Considerations

Can be landfilled or incinerated, when in compliance with local regulations.

14. Transport Information

Not classified as dangerous in the meaning of transport regulations.

15. Regulatory Information

- **U.S. FEDERAL REGULATIONS**

TSCA Inventory Status: In compliance with TSCA Inventory requirements for commercial purposes.

16. Other Information

- **ADDITIONAL INFORMATION**

Do not use in medical applications involving permanent implantation in the human body.

We hereby certify that the above statements are accurate.

Signature/Issued Date:

Staron® solid surfaces

Samsung SDI

This Technical Bulletin is intended to provide guidelines for optimal fabrication, installation, and performance of Samsung products mentioned. Though the information contained herein is deemed reliable, none of the contents--including but not limited to the instructions, techniques, graphics, and recommendations--is to be understood as implying legal liability of fitness for a specific purpose, any other type of warranty, or being complete or absolute in its range and nature of information.

Depending on the user's particular application, all necessary measures must be taken to verify and test the adequacy for such needs or application. Any information or recommendation herein is strictly for purposes of reference and as such, Samsung SDI assumes no responsibility for its suitability or accuracy or the use of such information for products other than Samsung Staron® solid surfaces & Radianz® quartz surfaces.