

## 1. Test method

- Apply 3 drops of each chemical reagent on the surface of staron® Solid Surfaces
- Expose the sample for 16 hours; covered with glass plate and uncovered
- Check the surface and scrub the surface with a wet Scotch-Brite® Pad and bleaching cleanser such as Ajax®

## 2. Test result

The residue from the following chemical reagents can be removed with a wet Scotch-Brite® pad and bleaching cleanser.

- |   |                                 |
|---|---------------------------------|
| - Acetic acid (10%)                       | - Acetone                       |
| - Ammonia                                 | - Ammonium hydroxide (5,28%)    |
| - Amyl acetate                            | - Amyl alcohol                  |
| - Ball point pen                          | - Benzene                       |
| - Bleach (household type)                 | - Blood                         |
| - B-4 body conditioner                    | - Butyl alcohol                 |
| - Carbon disulfide                        | - Carbon tetrachloride          |
| - Citric acid (10%)                       | - Calcium thiocyanate (78%)     |
| - Cigarette (nicotine and tar)            | - Coffee                        |
| - Cooking oils                            | - Cottonseed oil                |
| - Cupra ammonia                           | - Dishwashing liquid/powders    |
| - Ethanol                                 | - Ethyl acetate                 |
| - Ethyl ether                             | - Formaldehde                   |
| - Gasoline                                | - Gentian violet                |
| - Grape juice                             | - Hair dyes                     |
| - Household soaps                         | - Hydrochloric acid (20,30,37%) |
| - Hydrogen peroxide                       | - Iodine (1%)                   |
| - Ketchup                                 | - Lemon juice                   |
| - Lipstick                                | - Mercurochrome (2%)            |
| - Methanol                                | - Methyl ethyl ketone           |
| - Methyl orange (1%)                      | - Methyl red (1%)               |
| - Mineral oil                             | - Mustard                       |
| - Nail polish                             | - Naphthalene                   |
| - N-hexane                                | - Olive oil                     |
| - Pencil lead                             | - Perchloric acid               |
| - Permanent marker pen                    | - Shoe polish                   |
| - Soapless detergents                     | - Sodium bisulfate              |
| - Sodium hydroxide solution (5,10,25,40%) | - Soy sauce                     |
| - Sodium sulfate                          | - Sulfuric acid (25,33,60%)     |
| - Sugar (sucrose)                         | - Tea                           |
| - Sulfuric acid (25,33,60%)               | - Toluene                       |
| - Tetrahydrofuran                         | - Urea (6%)                     |
| - Tomato juice                            | - Vinegar                       |
| - Uric acid                               | - Wine                          |
| - Washable inks                           | - Zinc Chloride                 |
| - Xylene                                  |                                 |

*This Technical Bulletin is intended to provide guidelines for optimal fabrication, installation, and performance of Samsung products mentioned. Though the information contained herein is deemed reliable, none of the contents--including but not limited to the instructions, techniques, graphics, and recommendations--is to be understood as implying legal liability of fitness for a specific purpose, any other type of warranty, or being complete or absolute in its range and nature of information.*

*Depending on the user's particular application, all necessary measures must be taken to verify and test the adequacy for such needs or application. Any information or recommendation herein is strictly for purposes of reference and as such, Samsung SDI assumes no responsibility for its suitability or accuracy or the use of such information for products other than Samsung Staron® solid surfaces & Radianz® quartz surfaces.*

## Chemical Resistance (Continued)

The following chemical reagents may affect the surface complete removal. Frequent and/or prolonged exposure to these reagents should be avoided.

- Acetic acid (90,98%)
- Acid drain cleansers
- Chlorobenzene
- Chloroform (100%)
- Chromic trioxide acid
- Cresol
- Dioxane
- Ethyl acetate
- Equalizing mix (50/50)
- Film developer
- Formic acid (50,90%)
- Furfural
- Glacial acetic acid
- Hydrofluoric acid (48%)
- Luralite mix (50/50)
- Methylene chloride based products such as paint removers, brush cleansers and some metal cleansers
- Nitric acid (25,30,70%)
- Phenol (40,85%)
- Phosphoric acid (75,90%)
- Sulfuric acid (77,96%)
- Trichloroacetic acid (10,50%)
- 3M Avagard™ D



*This Technical Bulletin is intended to provide guidelines for optimal fabrication, installation, and performance of Samsung products mentioned. Though the information contained herein is deemed reliable, none of the contents--including but not limited to the instructions, techniques, graphics, and recommendations--is to be understood as implying legal liability of fitness for a specific purpose, any other type of warranty, or being complete or absolute in its range and nature of information.*

*Depending on the user's particular application, all necessary measures must be taken to verify and test the adequacy for such needs or application. Any information or recommendation herein is strictly for purposes of reference and as such, Samsung SDI assumes no responsibility for its suitability or accuracy or the use of such information for products other than Samsung Staron® solid surfaces & Radianz® quartz surfaces.*